

## PHOTOVOLTAIC CELL OPERATION ON MARS

Geoffrey A. Landis and Thomas Kerslake  
NASA John Glenn Research Center  
mailstop 302-1  
21000 Brookpark Road  
Cleveland, OH 44135 USA  
phone: 1-216-433-2238  
fax: 1-216-433-6106  
e-mail: geoffrey.a.landis@nasa.gov

Phillip P. Jenkins and David A. Scheiman  
Ohio Aerospace Institute  
mailstop 302-1, 21000 Brookpark Road  
Cleveland, OH 44135 USA

**ABSTRACT:** The Martian surface environment provides peculiar challenges for the operation of solar arrays: low temperature, solar flux with a significant scattered component that varies in intensity and spectrum with the amount of suspended atmospheric dust, and the possibility of performance loss due to dust deposition on the array surface. This paper presents theoretical analyses of solar cell performance on the surface of Mars and measurements of cells under Mars conditions.

**Keywords:** Space, Space Cells

### 1 SOLAR CELLS ON MARS

Operation of solar cells on the Martian surface presents challenges significantly different from those of operating on either the Earth's surface or in orbit. For many proposed Mars probes, the performance of the solar arrays presents the main operational constraint on the allowed latitude of the landing site, on the amount of power available for science operations, and on how long during each day the scientific instruments can operate.


The environmental conditions on the surface of Mars are quite different from the orbital environment in which space solar arrays normally operate [1]. Major differences of the Martian surface from operating conditions of Earth orbit are:

- lower solar intensity due to greater distance of Mars from the sun
- suspended atmospheric dust modifies the solar spectrum and reduces intensity [2-5]
- low operating temperatures
- deposition of dust on the arrays [6]

For Mars surface operation, radiation exposure is not a significant source of degradation.

The redder spectrum of Mars and the low operating temperature tend to favor lower bandgap solar cell technologies. Constraints due to shock and g-loading of the landing are also a factor, as well as flexure of the arrays due to wind. This will favor more robust cell substrate materials. The requirement for small array sizes for roving vehicles, on the other hand, drives the solar cell technology toward high-efficiency solar cell designs, since only a limited amount of array area is available. GaInP/GaAs/Ge triple-junction cells were the technology chosen for the Mars Exploration Rover mission (Figure 1), which landed on Mars in January 2004. (The British Mars

lander, Beagle-2, also chose triple-junction cells for the solar arrays, although the mission did not land successfully on Mars).




**Figure 1:** The Mars Exploration Rover (MER) vehicle, with five solar array panels.

### 2 SOLAR ENERGY


The solar energy on the Martian surface depends on the amount of dust in the atmosphere. Figures 2 and 3 show modeled results of the total solar flux reaching the surface at the MER-1 Gusev Crater landing site for two different dust conditions, a low dust opacity ( $\tau = 0.5$ ) and a high dust opacity ( $\tau = 0.95$ ). The graph shows both the direct and scattered components of the illumination. In the high-dust case, the direct illumination is reduced, while the scattered component is increased. (The actual atmospheric conditions at the landing site showed a

This is a preprint or reprint of a paper intended for presentation at a conference. Because changes may be made before formal publication, this is made available with the understanding that it will not be cited or reproduced without the permission of the author.

high optical depth, measured at about 0.9, at the landing, and the optical depth decreased during the mission to less than 0.5).




**Figure 2:** Sunlight on Mars (low dust case,  $\tau = 0.5$ ), showing the direct (circles), scattered (triangles), and total insolation on a horizontal surface during the course of a Martian sol.




**Figure 3:** Sunlight on Mars (high dust case,  $\tau = 0.95$ ).

The spectrum is significantly altered by the atmospheric dust. Figure 3 shows an example calculation, for the case of an optical depth  $\tau=1$ , and zenith angle zero degrees (noon), similar to the conditions at the MER rover sites near the landing day.

In addition, atmospheric dust settles on the solar array [6], both changing the spectrum and also reducing the performance as the mission duration increases



**Figure 4:** modelled solar spectrum on Mars surface (noon,  $\tau = 1$ ).



**Figure 5:** The rear panel of the solar array on the MER rover.

### 3 OPERATION OF SOLAR CELLS ON MARS


Following the successful use of solar power on the Mars Pathfinder mission, in which both the lander and the rover used GaAs solar cells for primary power, the Mars Exploration Rovers, "Spirit" and "Opportunity," demonstrated the first use of triple-junction GaInP/GaAs/Ge solar cells on the surface of Mars. One of the panels of the array is shown before flight in figure 5.

#### 3.1 Laboratory measurements


The solar cell performance will depend on the spectrum, intensity, and temperature of the arrays. For the triple-junction solar cells used on the MER solar arrays, the short-circuit current is limited by the top sub-cell of the three-cell stack. Figures 6 shows the quantum efficiency of the top GaInP solar cell used in the MER solar arrays, showing that it is primarily responding to the visible and blue spectral range, with a long-wavelength cut-off of about 650 nm (0.65 micrometers).

Figures 7 and 8 show the effect of temperature on the cell performance, showing measurements made at both 1 AU (Earth distance) and Mars intensity under simulated AM0 solar spectrum,






**Figure 6:** Measured external quantum efficiency of the top sub-cell of the MER rover solar array.



**Figure 7:** Effect of temperature on cell open circuit voltage at AM0 Earth solar intensity (top curves) and Mars solar intensity (bottom).




**Figure 8:** Effect of temperature on cell short-circuit current at AM0 Earth solar intensity (top) and Mars solar intensity (bottom).


### 3.2 Operation on Mars

As of 135 sols after the landing of Spirit on the surface of Mars, the solar arrays of both rovers are continuing to perform well on the surface of Mars. Figure 9 shows the right wing of the solar array, as viewed by the pancam on the surface of Mars. Figure 10 shows the operational result for the first full day on Mars, showing excellent performance of the triple junction cells under Mars conditions.


Dust deposition on the solar arrays is being measured, but is not currently a limiting factor on the array performance.



**Figure 9:** MER Solar array on Mars



**Figure 10:** Short circuit current during the first day on Mars



**Figure 11:** Future missions: The 2007 "Phoenix" mission to the Martian polar regions will use an advanced flexible solar array.

#### 4 REFERENCES

- [1.] G. Landis, "Solar Cell Selection for Mars," *IEEE Aerospace and Electronic Systems Magazine*, Vol. 15, No. 1, 17-21 (Jan. 2000). Presented at the 2nd World Conference on Photovoltaic Energy Conversion, Vol. III, Vienna, Austria, July 1998, 3695-3698.
- [2.] R. Haberle, C.P. McKay, O. Gwynne, D. Atkinson, G. Landis, R. Zurek, J. Pollack and J. Appelbaum, "Atmospheric Effects on the Utility of Solar Power on Mars," *Resources of Near Earth Space*, 799-818. U. Arizona Press Space Science Series (1993).
- [3.] J. Appelbaum, G. Landis and I. Sherman, "Solar Energy on Mars: Stationary Photovoltaic Array," *Journal of Propulsion and Power*, Vol. 11 No. 3, 554-561 (1995).
- [4.] J. Appelbaum and G. Landis, "PV Arrays for Martian Surface Power," *Acta Astronautica*, Vol. 30, 127-142 (1993); paper IAF-92-0591, 43rd IAF Congress (1992).
- [5.] J. Appelbaum, G. Landis and I. Sherman, "Sunlight on Mars: Update 1991," *Solar Energy*, Vol. 50 No. 1, 35-51 (1993).
- [6.] G. Landis and P. Jenkins, "Measurement of the Settling Rate of Atmospheric Dust on Mars by the MAE Instrument on Mars Pathfinder," *J. Geophysical Research*, Vol. 105, No. E1, 1855-1857 (Jan 25, 2000).
- [7.] R. E. Arvidson, *et al.*, "Physical Properties and Localization Investigations Associated With the 2003 Mars Exploration Rovers," *J. Geophysical Research: Planets*, 108. No. E2, 8070 (2003).